

PRECONSTRAINT

1202 S2 & 1202 FLUOTOP T2



1202-8636 S2



1202-1746 T2

| Technical properties | Précontraint 1202 S2 | Précontraint 1202 Fluotop T2 | Standards |
|------------------------------|---|---|--|
| Application | Mobile or permanent structures | Tropical climate , static and permanent structures | |
| Surface treatment (top/back) | PVDF / PVDF | HIGH CONCENTRATION PVDF / PVDF | |
| Making up | Weldable | Weldable after top surface abrasion | |
| Yarn | PES HT 1100/1670 Dtex | PES HT 1100/1670 Dtex | |
| Weight | 1050 g/sqm • 31 oz/sqyd | 1050 g/sqm • 31 oz/sqyd | EN ISO 2286-2 |
| Total thickness | 0.78 mm | 0.78 mm | |
| Width | 267 cm • 150.1 in | 178 cm • 70.08 in | (+1mm /-1mm) |
| Tensile strength (warp/weft) | 560/560 daN/5cm 565/565 lbs/in | 560/560 daN/5cm 565/565 lbs/in | EN ISO 1421 ASTM D 751-00 Cut Strip |
| Tear resistance (warp/weft) | 80/65 daN 130/110 lbs | 80/65 daN 130/110 lbs | DIN 53.363 ASTM D 751-00 Trapezoid |
| Adhesion | 12 daN/5cm | 12 daN/5cm | EN ISO 2411 |
| Flame retardancy | | | |
| Euroclass | B-s2,d0 /EN 1350-1 | B-s2,d0 /EN 1350-1 | |
| Rating | B1 /DIN 4102-1 • BS 7837 • Test2 /NFPA 701 • CSMF T19 | | |
| Guarantee* | | | |



> The technical data here above are average values with a +/-5% tolerance

| Longevity | | | | |
|---|------------------------------|--------------|-------------------------------|--|
| Coating thickness at the top of the yarns | 270 microns | | 270 microns | |
| Varnish adhesion longevity | QUV A 4000 h | pass | QUV A 4000 h | pass |
| White color evolution | QUV A 4000 h | ΔE = 5.5 | QUV A 4000 h | ΔE = 3.5 |
| Micro organism resistance ** | -- | | Method A: degree 0, excellent | EN ISO 846-A |
| Solar optical values | | | | |
| | ASHRAE | EN 410 | ASHRAE | EN 410 |
| Solar Transmittance (Ts) | 6% | 6% | 7% | 7% |
| Solar reflectance (Rs) | 75% | 80% | 74% | 79% |
| Solar Factor (g) | 11% | 10% | 12% | 11% |
| Visible light Transmittance (Tv) | -- | 4.5% | -- | 5% |
| Visible light Reflectance (Rv) | -- | 88% | -- | 87% |
| UV transmission | | T-UV 0% | | T-UV 0% |
| Visible light Transmittance (Tv) | 9.5% | | 10% | NFP 38511 (diffus-diffus) |
| Global thermal conductivity*** | | | | |
| Vertical / Horizontal position | U= 5.6 / 6.4 W/sqm/°C | | U= 5.6 / 6.4 W/sqm/°C | |
| Acoustic performance | | | | |
| Weakening index | 14dBA | | 14dBA | |
| | | | ISO 717-1 | |
| LEED Heat island Effect | | | | |
| Non roof (up to 2 pts) | Solar Reflectance Index >95% | | Solar Reflectance Index >95% | |
| Roof (up to 1 pt) | Solar Reflectance Index >95% | | Solar Reflectance Index >95% | |
| | | | SSc 7.1 | |
| | | | SSc 7.2/GIB C9 (ND) | |
| Environmental Impact: LCA (Life Cycle Assessment) | | | | |
| | ISO 14041-44 | | | |
| Comparative analysis depending on end-of-life scenarios | Texyloop® Recycling | Incineration | Landfill | Functional unit = 1 sqm Material only / 1202 S2 values |
| Resources depletion | 0.023 | 0.140 | 0.140 | Kilograms eq. Sb |
| Global warming | 2.60 | 4.846 | 4.193 | Kilograms eq. CO ₂ |
| Energy consumption | 60.2 | 107.1 | 107.1 | Megajoul eq. |
| Water consumption | 140.3 | 333.1 | 331.3 | Litre |
| Management systems | | | | |
| Quality in conformity with | ISO 9001 | | | |
| Environmental communication in conformity with | ISO 14021 | | | |
| Certifications, labels, recycling capacity | | | | |



LCA and LEED reports (S2 and T2) available on request

> The values here above are given as an indication in order to allow our customers to make the best use of our products. Our products are subjects to evolutions due to technical progress, we remain entitled to modify the characteristics of our products at any time. The buyer of our products is responsible to check that the here above data are still valid.

* Warranty: Please refer to the text of our warranty. The warranty is valid only after confirmation on case-by-case basis of warranty application. The warranty will not apply to mobile structures.

** See long term case studies in tropical climate (Longevity & sustainability brochure).

*** Those data are obtained by calculation through simulations of the average conditions of use, those values must be considered as approximation.

The buyer of our products is fully responsible for their application or their transformation concerning any possible third party. The buyer of our products is responsible for their implementation and installation according to the standards, use and customs and safety rules of the countries where they are used.

→ Contact

- Headquarters: + 33 (0)4 74 97 41 33
- Your local representative:
www.sergeferrari.com

→ TEXYLOOP®

- The Serge Ferrari operational recycling chain
- Secondary raw materials of high intrinsic value compatible with multiple processes
- A quantified response to combat depletion of natural resources

www.texyloop.com

www.sergeferrari.com

Join us
facebook.com/SergeFerrariGroup

Serge Ferrari