

Handling, Installation and Maintenance SHEERFILL®, FABRASORB® AND SGM™ Membrane

Handling – During fabrication and installation, care must be taken to eliminate hard creases which will damage the fiberglass yarns. Walking, stepping on or applying weight to any fold must be avoided. Maintaining a radius of curvature of 4 to 6 inches (100 to 150 mm) in any folded area of the fabric is highly recommended.

These same precautions should be taken after the fabric panels are fabricated into larger panels. The increase in total weight of the fabricated panels should be taken into account when folding the panels for shipment to a construction site. All folds should be padded to maintain the 4 to 6 inch (100 to 150 mm) radius of curvature.

The membrane must not be dragged across floors that do not have a smooth finish. The Teflon® coating can be damaged by the rough surface, exposing fiberglass to the environment which will have an effect on the life of the finished structure.

Installation – The same care of the membrane should be taken during the installation process. Uncrating of the fabricated membrane should be done carefully to avoid any sharp surfaces as the membrane is moved from the crate to its final area for installation. These potentially rough surfaces can be found on the ground or on any steel structure over which the membrane is placed. Industry standards should be followed for tensioning the membrane into its final prestressed state.

Maintenance – The installed membrane should be examined on a scheduled basis (at least once a year). In most cases the membrane will not need any cleaning. However, if the membrane or anything close to the membrane requires cleaning, great care should be taken in the choice of cleaners. Only pure soap products (i.e., Murphy® Oil Soap*) should be used. Any other cleaners or solvents, which contain chemicals that will reduce the surface tension of water, will damage the membrane.

SHEERFILL® and FABRASORB® are registered trademarks of Saint-Gobain Performance Plastics Corporation
TEFLON® is a registered trademark of E.I. Dupont de Nemours
Murphy® Oil Soap is a registered trademark of Colgate-Palmolive Company

* If not available in your area, contact Saint-Gobain for sourcing information.

RevA



Saint-Gobain Performance Plastics

701 Daniel Webster Highway
Merrimack, NH 03054

Tel: +1 603 420 1250
Fax: +1 603 424 9012

sheerfill@saint-gobain.com
www.sheerfill.com



NOTE: Saint-Gobain Performance Plastics Corporation does not assume any responsibility or liability for any advice furnished by it, or for the performance or results of any installation or use of the product(s) or of any final product into which the product(s) may be incorporated by the purchaser and/or user. The purchaser and/or user should perform its own tests to determine the suitability and fitness of the product(s) for the particular purpose desired in any given situation.