

SHEERFILL® II

SHEERFILL® II Architectural Membrane

SHEERFILL® is the trademark for a family of membranes used in permanent structures. The composite is made of fiberglass and polytetrafluoroethylene (PTFE). SHEERFILL products are available in a range of strengths and light transmission levels, providing the user with a choice of membranes to cover virtually any size structure from a full-sized stadium to a relatively small skylight. All SHEERFILL membranes conform to rigid fire and building codes for permanent buildings.

Saint-Gobain Performance Plastics

701 Daniel Webster Highway
Merrimack, NH 03054

Tel: +1 603 420 1250
Fax: +1 603 424 9012

sheerfill@saint-gobain.com
www.sheerfill.com

Typical Properties¹

Property	Value	Method
Coated Fabric Weight (oz./yd. ²)	38.5 nominal	ASTM D4851-88
Thickness (inches)	0.030 nominal	ASTM D4851-88
Breaking Strength (lb./in.) (Strain Rate: 2 in./min.)		ASTM D4851-88
Dry, Warp	825 min. avg.	
Dry, Fill	600 min. avg.	
Breaking Strength After Crease Fold (lb./in.)		ASTM D4851-88
Dry, Warp	680 min. avg.	
Dry, Fill	415 min. avg.	
Trapezoidal Tear (lb.)		ASTM D4851-88
Warp	75 min. avg.	
Fill	70 min. avg.	
Solar Transmission (%)	12 nominal	ASTM E424
Solar Reflectance (%)	73 nominal	ASTM E424
Burning Characteristics		
Flame Spread	5 max	ASTM E84
Smoke Generation	10 max	Tunnel Test
Incombustibility of Substrates	Pass	ASTM E136
Fire Resistance of Roof Coverings	Class A	ASTM E108
Spread of Flame and Intermittent Flame		
Flame Resistance	Pass	NFPA 701, Small Scale
Color	White (after exposure to sunlight)	—
Reinforcement Construction	Warp β150 4/2 Fill β150 4/2	Count W24 x F19.5

¹Values listed are for virgin roll goods only. Appropriate industry safety factors need to be used to account for the in-service effects of handling, weathering, etc.



Listed
product ID #15803-2



Limited Warranty: For a period of 6 months from the date of first sale, Saint-Gobain Performance Plastics Corporation warrants this product(s) to be free from defects in manufacturing. Our only obligation will be to provide replacement product for any portion proving defective, or at our option, to refund the purchase price thereof. User assumes all other risks, if any, including the risk of injury, loss or damage, whether direct or consequential, arising out of the use, misuse, or inability to use this product(s). SAINT-GOBAIN PERFORMANCE PLASTICS DISCLAIMS ANY AND ALL OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.

NOTE: Saint-Gobain Performance Plastics Corporation does not assume any responsibility or liability for any advice furnished by it, or for the performance or results of any installation or use of the product(s) or of any final product into which the product(s) may be incorporated by the purchaser and/or user. The purchaser and/or user should perform its own tests to determine the suitability and fitness of the product(s) for the particular purpose desired in any given situation.

Valid 01/2013
Supersedes all previous versions.

SHEERFILL® is a registered trademark.
©2013 Saint-Gobain Performance Plastics Corporation
AFF-1712-0613-SGCS

